

Image Cover Sheet

CLASSIFICATION

UNCLASSIFIED

SYSTEM NUMBER

511921



TITLE

Fatigue Crack Initiation and Growth in A517 SAW Weldments Under Variable Amplitude Loading

System Number:

Patron Number:

Requester:

Notes: Paper #47 contained in Parent sysnum #511874

DSIS Use only:

Deliver to: CL

Fatigue Crack Initiation and Growth in A517 SAW Weldments Under Variable Amplitude Loading

by Christopher Bayley¹ and John Porter²

¹Fleet Technology Ltd, Kanata Ontario

²Defence Research Establishment Atlantic, Dockyard Laboratory (Atlantic)
P.O. Box 99000 Stn Forces, Halifax, NS B3K 5X5

ABSTRACT

A comparison between experimental and analytical predicted fatigue lives is made for a A517 SAW Weldment subjected to variable amplitude loading. Three, 10 inch wide butt-welded specimens were tested under a variable amplitude load spectrum consisting of 3 yearly storms. The magnitude of the loads in the storm increased and then decreased in a linear manner with the winter storm representing the most severe loading condition. Fatigue crack monitoring was achieved through the use of 20 localized potential drop probes affixed along the length of the weld. Multiple and independent fatigue crack initiation sites were found along the length of the weld. These eventually coalesced and formed a dominant fatigue crack, which led to the eventual failure of the specimens.

Fatigue life estimates using local notch strain and fracture mechanics approaches were obtained. Fatigue crack initiation life estimates using the strain life approach were found to be un-conservative while the estimates of the fatigue crack propagation life were conservative. Accurate knowledge of the structural and weld geometries was found to be critical in the estimation of the fatigue lives.



Fatigue Crack Initiation and Growth in A517 SAW Weldments

By: Christopher Bayley FTL

John Porter DREA

May 13 1999

FTL FLEET
TECHNOLOGY LTD.



Objectives

- **Effects of Variable Amplitude Load Spectrum on Fatigue Crack Initiation, Propagation and Coalescence**
- **Generate Experimental data on Fatigue Initiation and Propagation**
- **Compare Experimental and Numerical Fatigue Crack Predictions**

FTL FLEET
TECHNOLOGY LTD.


Experimental Work

■ Material Properties

- Cyclic Stress/Strain Curves
- Fatigue Crack Initiation
- Fatigue Crack Growth

■ Weld Residual Stresses

■ Variable Amplitude Tests on 10" Wide Specimens



FTL FLEET
TECHNOLOGY LTD.

Material

■ 10 mm A517 SAW Material Received from Dockyard Labs


■ Representative of the Deck Material used in the Halifax Class Patrol Frigates

■ Samples

- 6 Round Specimens
- 3 Center Crack Panels
- 3 10" Wide Specimens for VA Tests


FTL FLEET
TECHNOLOGY LTD.

Material Properties Cyclic Stress Strain Curve




FTL FLEET
TECHNOLOGY LTD.

Material Properties Fatigue Crack Initiation




FTL FLEET
TECHNOLOGY LTD.


Material Properties Fatigue Crack Growth



Variable Amplitude Tests Fatigue Specimens




Specimen Characterization Specimen Preparation





FTL FLEET
TECHNOLOGY LTD.



Specimen Characterization Hot Spot Stress



FTL FLEET
TECHNOLOGY LTD.




Variable Amplitude Tests Crack Monitoring




FTL FLEET
TECHNOLOGY LTD.

Variable Amplitude Tests PD Time History




FTL FLEET
TECHNOLOGY LTD.

Variable Amplitude Tests Beachmarks




Variable Amplitude Tests Fatigue Crack Initiation Sites



Fatigue Crack

Initiation Points


Cycles →



Crack Depth (mm)

Plate Width (254 mm)

Variable Amplitude Tests Crack Shape Development




FTL FLEET
TECHNOLOGY LTD.

Analytical Approach

- Fatigue Crack Initiation and Propagation Software
FALIN and FALPR
- Work Completed by: Dr Gregory Glinka University of
Waterloo, Waterloo Ontario
- Stress Life (SN) Approach
- Strain Life (ϵN) Approach
- Fatigue Crack Growth (da/dN)

FTL FLEET
TECHNOLOGY LTD.


Analytical Approach Stress Life



- BS-5400 'D' Detail Weld Transverse to Principle Stress dir.
- Miner's Summation used to sum damage from individual cycles
- Significant Damage Caused by Small Stress Ranges

FTL FLEET
TECHNOLOGY LTD.


Analytical Approach Strain Life




- Local Strain Approach accounts for:
- Geometry of the notch
- Angular Distortion and Straightening of Plates
- Membrane and Bending Components
- Residual Stress State
- Hot Spot Stress

FTL FLEET
TECHNOLOGY LTD.


Analytical Approach Fatigue Crack Growth



Results Experimental & Numerical



Results Experimental & Numerical



FTL FLEET
TECHNOLOGY LTD.

Conclusions Numerical

- S-N VERY Conservative
- ϵ -N Over-Predicts Fatigue Initiation
 - Requires detailed information specific to each geometry
- Fatigue Crack Growth
 - Conservative if omit Retardation effects

FTL FLEET
TECHNOLOGY LTD.

Conclusions Experimental

- Fatigue Crack Initiation accounts for 70% of Total Fatigue Life
- Variable Amplitude Loading affects the Number of Initiation Sites
- Fatigue Life Affected by:
 - Hot Spot Stress Concentration
 - Notch Geometry
 - Angular Distortion of Specimens
 - Load Spectrum

FTL FLEET
TECHNOLOGY LTD.

Recommendations Future Research

- Determine the influence of weld shape and residual strains on the fatigue performance of butt welded joints
- Variable and Constant Amplitude Tests
- Weld Toe Improvements and Fatigue Life
- Examine Agreement between Numerical Predictions and Experimental tests

FTL FLEET
TECHNOLOGY LTD.